



**COREFACTOR EIFS - System Performance**  
**Testing Summary**

<b>TEST</b>	<b>METHOD</b>	<b>RESULTS</b>
Accelerated Weathering	CCMC 07240, Section 6.9 and ASTM G-26 Xenon Arc Method	PASS, No cracking, flaking or deleterious effects after 2000 hours.
Freeze-Thaw Resistance	ICBO AC24	PASS, 10 cycles
Water Vapour Permeance	ASTM E-96 Desiccant Method	PASS, > 170 ng/ Pa·s·m <sup>2</sup>
Water Penetration	ASTM E-331	PASS, No water penetration after 15 minutes at 6.24 psf.
Water Impermeability	CCMC 07240, Section 6.6	PASS, No dampness after 2 hours.
Drainage Performance on DuPont Tyvek® StuccoWrap® Weather Resistant Barrier.	ICBO AC24 and EIMA 200.2	PASS, Average drainage efficiency: 99.3%
Salt Spray Fog Resistance	ASTM B-117	PASS, No cracking, flaking or deleterious effects.
Mildew and Fungal Resistance	MIL 810-E, Method 508.4	PASS, No fungal or mildew development on surface.
Structural Performance	ASTM E-330	Maximum positive and negative wind loads for different fastening configurations are available upon request.
Impact Resistance	CCMC 07240, Section 5.6.2	PASS, No perforations or cracks, through which the mesh can be seen.
Fire Resistance	CAN/ULC S114-M80, Non-combustibility in Building	PASS
	CAN/ULC S101-M89 and ASTM E-119, 15 minutes stay in place.	PASS
	CAN/ULC S134-92, Full Scale Fire Test	PASS