



## GLASS BLOCK MORTAR

### Testing Summary

TEST	METHOD	CRITERIA (according to the 2000 IBC Code)	RESULTS
<b>Compressive Strength:</b>			
At 7 days	ASTM C-270	na	1452
At 28 days		>1800 psi	2155
<b>Water Retention:</b>			
Air Content	ASTM C-231	<12%	11%
Time of Set	ASTM C-807	na	180 minutes
Water Absorption	In-House Immersion Method	na	14.60%
At 28 days			