



## PREMIX, PREMIX 1000, PREMIX ARTISAN

### **Finish Coat Stucco**

PROPERTY	TEST METHOD	RESULTS
<b>WATER VAPOUR TRANSMISSION</b>		
<i>Water vapour permeance for:</i>		
Premix, ng/Pa.s.m <sup>2</sup> (perms)	ASTM E-96 Desiccant Method Procedure A	1488 (26)
<b>COMPRESSION STRENGTH</b>		
	ASTM C - 109	900 psi - 7 days 1200 psi - 28 days
<b>WATER ABSORPTION (IMMERSION)</b>		
Water absorption, %	ASTM C - 642	7.3 - 28 days
<b>SPECIFIC GRAVITY</b>		
	ASTM C - 642	1.76 - 28 days

### **IMASCO MINERALS INC.**

19287-98A Avenue, Surrey, BC V4N 4C8  
www.imascominerals.com

t: 604.888.3848  
f: 604.888.5671  
e: imasco@imascominerals.com